



LUMBER DESIGN VALUES FOR U.S.


LUMBER DESIGN VALUES

**For Use in the U.S.
Approved by the
American Lumber Standard Committee
Board of Review**


July 2006

900. LUMBER DESIGN VALUES

Recommended design procedures and allowable unit stresses for lumber manufactured under this Rule have been developed for use in the United States.



Lumber design values are regularly reviewed to reflect the latest available information on the physical properties of wood. The recommended allowable unit stresses published in this document have been reviewed by the U.S. Forest Products Laboratory and approved by the American Lumber Standard Committee Board of Review. Users should take care to ensure that they are using the latest published design values.



Recommended allowable unit stresses are developed in conformance to the American Softwood Lumber Standard, PS20 and are given in Paras. 905a. to 905o.

Load and Resistance Factor Design Values

The design values tabulated in Paras. 905i to 905o, as well as in Para. 910, are for use in the United States with Allowable Stress Design (ASD). More recently, a new design method called Load and Resistance Factor Design (LRFD) has been developed in the United States. The design values for LRFD, called reference strength, can be computed by multiplying the ASD design values by the factors listed in the following table:

LUMBER DESIGN VALUES FOR U.S.

Conversion Factors for LRFD Calculation

Extreme Fiber in Bending " F_b "	Tension Parallel to Grain " F_t "	Horizontal Shear " F_v "	Compression Perpendicular to Grain " $F_{C_{perp}}$ "	Compression Parallel to Grain " $F_{C_{ }}$ "	Modulus of Elasticity " E "
2.54	2.70	2.88	2.08	2.40	1.00

905. DESIGN VALUES FOR THE U.S.

905a. Recommended allowable unit stresses found in Paras. 905a. to 905o. of this section of the rules apply to lumber of species and combinations of species manufactured and shipped by mills in Canada for use in the United States. The values are calculated in accordance with the requirements of "Standard Practice for Establishing Allowable Properties for Visually Graded Dimension Lumber from in-Grade Tests of Full Size Specimens," ASTM D1990; and, where applicable, "Methods for Establishing Clear Wood Strength Values," ASTM D2555, and "Standard Practice for Establishing Structural Grades and Related Allowable Properties for Visually Graded Lumber," ASTM D245; published by ASTM and in accordance with the requirements of Voluntary Product Standard PS 20, American Softwood Lumber Standard.

The allowable unit stresses shown herein are recommended for use in design for all normal construction. Higher and lower design stresses may be used to meet special structural requirements. The "National Design Specification for Wood Construction" published by the American Wood Council (AWC), sets forth design methods for normal and most special structural uses.

Recommended design values are assigned to six basic properties of wood. These are fibre stress in bending (F_b), tension parallel to the grain (F_t), horizontal shear (F_v), compression parallel to grain ($F_{C_{||}}$), compression perpendicular to grain ($F_{C_{perp}}$), and modulus of elasticity (E).

Four of the above-mentioned lumber design properties relate directly to safety. These are fibre stress in bending (F_b), tension parallel to grain (F_t), compression parallel to grain ($F_{C_{||}}$) and horizontal shear (F_v). For dimension lumber, four of the above-mentioned properties are derived from full-size tests of commercially graded lumber ("In-grade" tests).

LUMBER DESIGN VALUES FOR U.S.

These are fibre stress in bending (F_b), tension parallel to grain (F_t), compression parallel to grain ($F_{c||}$), and modulus of elasticity (E). The other two properties, and all properties for timbers, are based on tests of clear wood for the various species.

Modifications are then made, in accordance with ASTM standards for moisture content, factors of safety and duration of load. For the clear wood case, values are further reduced to reflect the effects of grade characteristics (see ASTM D2555 & D245). During In-grade testing, species combinations were sampled from production; or, in the case of Northern Species, as individual species, which were grouped together using the criteria of ASTM D1990. For timbers, the grouping procedures of ASTM D2555 were followed.

The modulus of elasticity " E " is an experimental constant or ratio of the amount a material will deflect in proportion to an applied load. It, along with the moment of inertia, may be used to predict how much a member will deflect. It is a measure of stiffness and not a strength property or working stress, so is not related to safety except when used in column design where the listed averages shown herein are reduced more than three times in design formulas and computation. The tabulated " E " values in this book are average values and individual pieces having values both above and below the listed average occur in all lumber grades. For all normal construction, use of these average " E " values provides a conservative prediction of deflections which occur in wall, floor and roof assemblies. Tests by government, university and private research organizations show that deflections occurring when loads are applied to members in load sharing systems are less than predicted for single members. In such applications, the effect of a number of members sharing the load, together with the stiffening effects of fastenings and coverings, more than offset the variations inherent between the individual pieces.

The recommended " E " values for dimension lumber and decking shown in the tables of Paras. 905i. to 905m. apply to dry use of lumber manufactured in either dry or unseasoned condition. Recommended " E " values for Beams and Stringers and for Posts and Timbers shown in the tables of Paras. 905n. and 905o., apply to both wet and dry use of lumber manufactured in either dry or unseasoned condition.



LUMBER DESIGN VALUES FOR U.S.

For dimension lumber, values are based on In-grade testing and for timbers, values are derived from clear wood testing. The mean “E” values for various species based on the two test methods are comparable. Table 905h. compares “E” values for Select Structural grade, as an example.

In these rules, the various grades used for construction purposes are divided into size categories according to the principal end uses. The allowable unit stresses for these major grade categories are tabulated in Paras. 905i. to 905o. The tables show recommended design values for engineered use as single members, for normal duration of load in pounds per square inch. Adjustment of these values for other conditions of loading and the criteria for their use in the design of structures are outlined in the current “National Design Specification for Wood Construction,” which is available from the American Wood Council (AWC)

Bending values, for all size categories except Decking and Scaffold Plank apply to pieces loaded on the narrow face as joists, rafters, or beams. For all categories except Beams and Stringers, Para. 905d. contains adjustment factors for pieces loaded on the wide face as plank or decking.

905b. ENGINEERING DESIGN VALUES

The recommended design values are derived from data or calculations that include consideration of the maximum strength reducing characteristics allowed in the grade. The values are premised on the assumption of the individual member carrying its own design load.

905c. REPETITIVE MEMBER DESIGN VALUES

In actual practice, only a few pieces will contain the maximum strength reducing characteristics permitted in the grade. Therefore, most of the pieces will have actual values higher than the assigned engineering value and when these pieces are used together in a repetitive member system, a 15% increase factor is allowed for fibre stress in bending.

A repetitive member system is defined as 3 or more framing or supporting members, such as joists, studs, planks or decking, that are adjacent or are spaced not more than 24-inches and are joined by floor, roof, or other load-distributing elements.

LUMBER DESIGN VALUES FOR U.S.

905d. FLATWISE USE OF LUMBER

Tabulated values are based on edgewise use for grades of Light Framing, Structural Light Framing, Studs, or Structural Joists & Planks, as well as for Machine Graded Lumber. When used flatwise rather than on edge, the allowable fibre stress in bending may be multiplied by the factors in the following table:

ADJUSTMENT FACTORS FOR FLATWISE USE (Apply to allowable fibre stress in bending)

Width	Nominal Thickness	
	2" & 3"	4"
<4"	1.00	1.00
4"	1.10	1.00
5"	1.10	1.05
6"	1.15	1.05
8"	1.15	1.05
10" & Wider	1.20	1.10

These factors apply to all dimension lumber except for Scaffold Plank and Decking grades.

For Decking, the following adjustments may be used:

Nominal Thickness	2"	3"	4"
Flat-Use Factor	1.10	1.04	1.00

ADJUSTMENT FACTORS FOR BEAMS AND STRINGERS SUBJECTED TO LOADS APPLIED TO THE WIDE FACE

Grade	Factors		
	Bending "F _b "	Modulus of Elasticity "E"	Other Properties
Sel Str	0.86	1.0	1.0
No. 1	0.74	0.9	1.0
No. 2	1.0	1.0	1.0

905e. EFFECT OF MOISTURE CONTENT ON DESIGN VALUES

The design values shown in the tables in Paras. 905i. to 905o., are applicable to lumber that will be used under dry conditions such as in most covered structures. The section properties of lumber for use in design should be based on the surfaced sizes shown in these rules.

For 2" to 4" thick lumber, the dry surfaced size should be used.

16

LUMBER DESIGN VALUES FOR U.S.

In calculating design values, the natural gain in strength and stiffness that occurs as lumber dries has been taken into consideration as well as the reduction in size that occurs when unseasoned lumber shrinks. The gain in load carrying capacity due to increased strength and stiffness resulting from drying offsets the design effect of size reductions due to shrinkage. By adjusting design values to compensate for loss in size by shrinkage of unseasoned lumber, use of the surfaced sizes shown is possible and design is simplified.

Because of the built-in adjustments explained above, dry surfaced sizes should be used for design purposes in all instances. There are two situations where the tabulated design values should be adjusted:

i) M.C. Adjustment Factors for Nominal 2" to 4" Thick Lumber

(Use only when moisture content will exceed 19% in use)

When 2" to 4" thick dimension lumber or decking is designed for exposed uses where the moisture content will exceed 19% for an extended period of time, the design values shown in the tables in Paras. 905i to 905m should be multiplied by the following adjustment factors:

Bending "F _b "	Tension "F _t "	Compression Parallel to Grain "F _{cl} "	Horizontal Shear "F _v "	Compression Perpendicular to Grain "F _{C_{perp}} "	Modulus of Elasticity "E"
0.85*	1.0	0.8 *	0.97	0.67	0.9

* Where the size-adjusted bending value (F_b x size factor) does not exceed 1150 psi, or the size-adjusted compression value (F_C x size factor) does not exceed 750 psi, a factor of unity may be used.

ii) M.C. Adjustment Factors for Nominal 5" and Thicker Lumber

(Use only when moisture content will exceed 19% in use)

When lumber 5" and thicker is designed for exposed uses where the moisture content will exceed 19% for an extended period of time, the design values shown in the tables in Paras. 905n. and 905o. should be multiplied by the following adjustment factors:

LUMBER DESIGN VALUES FOR U.S.

Bending "F _b "	Tension "F _t "	Compression Parallel to Grain "F _c "	Horizontal Shear "F _v "	Compression Perpendicular to Grain "F _{c⊥} "	Modulus of Elasticity "E"
1.00	1.00	0.91	1.00	0.67	1.00

905f. HORIZONTAL SHEAR DESIGN VALUES FOR LUMBER & TIMBERS

Shear design values for lumber have recently been revised and approved by the American Lumber Standard Committee, in accordance with changes to ASTM Standard D245, **Establishing Structural Grades and Related Allowable Properties for Visually Graded Lumber**. These new lumber shear design values are higher than earlier assigned values and are shown in the tables in Paras. 905i to 905o.

Revisions have also been made to design equations for use with the new shear design values. These equations no longer include increase factors to account for splits or checks in the lumber, and the notching equations have been revised. For further information, see American Wood Council website: www.awc.org

905g. ADJUSTMENT FACTOR FOR WIDTH

- i) Tabulated design values for dimension lumber apply to 12" width for Structural Joists and Planks, and Structural Light Framing. For all other sizes of these grades, use the following adjustment factors:

Width (Depth)	Bending		Tension Parallel to Grain	Compression Parallel to Grain	All Other
	<4" thick	4" thick			
≤ 4"	1.5	1.5	1.5	1.15	1.0
5"	1.4	1.4	1.4	1.1	1.0
6"	1.3	1.3	1.3	1.1	1.0
8"	1.2	1.3	1.2	1.05	1.0
10"	1.1	1.2	1.1	1.0	1.0
12"	1.0	1.1	1.0	1.0	1.0
≥ 14"	0.9	1.0	0.9	0.9	1.0

16

LUMBER DESIGN VALUES FOR U.S.

ii) Tabulated values for Light Framing grades (Construction, Standard, Utility) apply to 4" and narrower lumber, except that values for Utility grade apply only to 2" by 4" lumber.

iii) Tabulated design values for Stud grade apply to 5" and 6" widths. For 6" and narrower Stud grade, use the factors listed below. For Stud grade lumber wider than 6", use the property values for No.3 grade (Table 905i) and width adjustment factors as listed in Table 905g(i) above.

Width (Depth)	Bending	Tension Parallel to Grain	Compression Parallel to Grain	All Other
≤4"	1.1	1.1	1.05	1.0
5" to 6"	1.0	1.0	1.0	1.0

905h. MODULUS OF ELASTICITY

Select Structural Values* (Para. 124)

Species Group	Clear Wood Basis Dry E Values (psi)	In-Grade Basis Dry E Values (psi)
D Fir - L (N)	1,800,000	1,900,000
Hem-Fir (N)	1,500,000	1,700,000
S-P-F	1,500,000	1,500,000
Northern Species	1,100,000	1,100,000

* The In-grade "E" values were derived from tests of dimension lumber; the clear wood values were derived for dimension lumber from tests of small clear specimens.

**905i. STRUCTURAL LIGHT FRAMING (2" to 4" Thick, 2" to 4" Wide)
& JOISTS AND PLANKS (2" to 4" Thick, 5" and Wider) (Para. 124)**

Recommended Allowable Unit Stresses (in psi) - 2" by 12" Basis (for Size Adjustment Factors, see Para. 905g)

Species Group	Grade	Extreme Fibre in Bending F_b	Tension Parallel to Grain F_t	Horizontal Shear F_v	Compression		Modulus of Elasticity (million psi) E
					Parallel to Grain $F_{C }$	Perp. to Grain $F_{C\perp}$	
D Fir-L (N)	Select Structural	1350	825	180	1900	625	1.9
	No. 1 & Btr	1150	750		1800		1.8
	No. 1	850	500		1400		1.6
	No. 2	850	500		1400		1.6
	No. 3	475	300		825		1.4
Hem-Fir (N)	Select Structural	1300	775	145	1700	405	1.7
	No. 1 & Btr	1200	725		1550		1.7
	No. 1	1000	575		1450		1.6
	No. 2	1000	575		1450		1.6
	No. 3	575	325		850		1.4
S-P-F	Select Structural	1250	700	135	1400	425	1.5
	No. 1	875	450		1150		1.4
	No. 2	875	450		1150		1.4
	No. 3	500	250		650		1.2
Northern Species	Select Structural	975	425	110	1100	350	1.1
	No. 1	625	275		850		1.1
	No. 2	625	275		850		1.1
	No. 3	350	150		500		1.0

LUMBER DESIGN VALUES FOR U.S.

269

**905i. (cont.) STRUCTURAL LIGHT FRAMING (2" to 4" Thick, 2" to 4" Wide)
& JOISTS AND PLANKS (2" to 4" Thick, 5" and Wider) (Para. 124)**

Recommended Allowable Unit Stresses (in psi) - 2" by 12" Basis (for Size Adjustment Factors, see Para. 905g)

Species Group	Grade	Extreme Fibre in Bending F_b	Tension Parallel to Grain F_t	Horizontal Shear F_v	Compression		Modulus of Elasticity (million psi) E
					Parallel to Grain $F_{c }$	Perp. to Grain $F_{c\perp}$	
Y Cedar (N)	Select Structural	1200	725	175	1200	540	1.6
	No. 1	800	475		1000		1.4
	No. 2	800	475		1000		1.4
	No. 3	475	275		575		1.2
C Sitka	Select Structural	1300	950	125	1200	455	1.7
	No. 1	925	550		1100		1.5
	No. 2	925	550		1100		1.5
	No. 3	525	325		625		1.4

905j. LIGHT FRAMING (2" to 4" Thick, 2" to 4" Wide) (Para. 122)

Recommended Allowable Unit Stresses (in psi) - 2" by 4" Basis (for Size Adjustment Factors, see Para. 905g)

D Fir-L (N)	Construction	950	575	180	1800	625	1.5
	Standard	525	325		1450		1.4
	Utility	250	150		950		1.3
Hem-Fir (N)	Construction	1150	650	145	1750	405	1.5
	Standard	650	350		1500		1.4
	Utility	300	175		975		1.3

LUMBER DESIGN VALUES FOR U.S.

905j. (cont.) LIGHT FRAMING (2" to 4" Thick, 2" to 4" Wide) (Para. 122)

Recommended Allowable Unit Stresses (in psi) - 2" by 4" Basis (for Size Adjustment Factors, see Para.905g)

Species Group	Grade	Extreme Fibre in Bending F_b	Tension Parallel to Grain F_t	Horizontal Shear F_v	Compression		Modulus of Elasticity (million psi) E
					Parallel to Grain $F_{c }$	Perp. to Grain $F_{c\perp}$	
S-P-F	Construction	1000	500	135	1400	425	1.3
	Standard	550	275		1150		1.2
	Utility	275	125		750		1.1
Northern Species	Construction	700	325	110	1050	350	1.0
	Standard	400	175		875		0.9
	Utility	175	75		575		0.9
Y Cedar	Construction	925	550	175	1200	540	1.3
	Standard	525	300		1050		1.2
	Utility	250	150		675		1.1
C Sitka	Construction	1050	650	125	1300	455	1.4
	Standard	600	350		1100		1.3
	Utility	275	175		725		1.2

Note: Values for Utility grade apply only to 2" by 4" lumber.

LUMBER DESIGN VALUES FOR U.S.

271

LUMBER DESIGN VALUES FOR U.S.

90% SELECT STRUCTURAL SCAFFOLD PLANK (Para. 180)

(1 1/4" and Thicker, 8" and Wider)

Recommended Allowable Unit Stresses (psi)
(No Width Adjustment Factors Apply)

Species	2" Maximum Nominal Thickness ¹ Wet Service Condition ²		3" Maximum Nominal Thickness ³ Wet Service Condition ⁴	
	Extreme Fibre in Bending (F _b) Single Member	Modulus of Elasticity E	Extreme Fibre in Bending (F _b) Single Member	Modulus of Elasticity E
D Fir-L (N)	2050	2,000,000	1550	1,700,000
Hem-Fir (N)	1450	1,700,000	1100	1,500,000
S-P-F	1350	1,500,000	1000	1,300,000
Hem-Tam(N)	1700	1,400,000	1300	1,300,000
W Hem (N)	1800	1,800,000	1350	1,600,000
C Sitka	1400	1,700,000	1050	1,500,000
P Pine	1450	1,400,000	1100	1,200,000
WW Pine	1250	1,400,000	925	1,300,000
R Pine	1250	1,300,000	950	1,100,000
EW Pine (N)	1300	1,400,000	975	1,300,000

- The standard dressed "Dry" sizes shall be used in all calculations for 2 inch nominal material.
- For "Wet" use conditions where the moisture content in service will exceed 19%, the values for 2 inch nominal thick planks shall be multiplied by the following adjustment factors:
Extreme fibre in bending, $F_b = 0.86$
Modulus of Elasticity, $E = 0.97$
- The actual manufactured sizes shall be used in all calculations for 3 inch nominal material.
- Values for 3 inch nominal material are not dependent on service conditions.

905I. STUDS (2" to 4" Thick, 2" to 6" Wide) (Para. 121)

Recommended Allowable Unit Stresses (psi) – 2" by 6" basis

(for Size Adjustment Factors, see Table 905g (iii)) (for Studs wider than 6", use the property values for the No. 3 grade (Table 905i) and width adjustment factors as listed in Table 905g(i))

Species Group	Grade	Extreme Fibre in Bending F_b	Tension Parallel to Grain F_t	Horizontal Shear F_v	Compression		Modulus of Elasticity (million psi) E
					Parallel to Grain $F_{c }$	Perpendicular to Grain $F_{c\perp}$	
D Fir-L (N)	Stud	650	400	180	900	625	1.4
Hem-Fir (N)	Stud	775	450	145	925	405	1.4
S-P-F	Stud	675	350	135	725	425	1.2
Northern Species	Stud	475	225	110	550	350	1.0
Y Cedar	Stud	625	375	175	650	540	1.2
C Sitka	Stud	725	450	125	675	455	1.4

LUMBER DESIGN VALUES FOR U.S.

273

905m. DECKING (2" to 4" Thick, 4" and Wider) (Para. 127 only)

Recommended Allowable Unit Stresses (psi) (No Width Adjustment Factors Apply)

Species	Grade	Extreme Fibre in Bending (F_b)	Compression Perpendicular to Grain F_{cperp}	Modulus of Elasticity E
		Single Member		
D Fir-L (N)	Select	1750	625	1,800,000
	Commercial	1450		1,700,000
Hem-Fir (N)	Select	1350	405	1,500,000
	Commercial	1100		1,400,000
Hem-Tam (N)	Select	1500	555	1,300,000
	Commercial	1250		1,100,000
S-P-F	Select	1200	425	1,500,000
	Commercial	1000		1,300,000
W Hem (N)	Select	1500	410	1,600,000
	Commercial	1300		1,400,000
Coast Sitka Spruce	Select	1250	455	1,700,000
	Commercial	1050		1,500,000
Ponderosa Pine	Select	1200	535	1,300,000
	Commercial	1000		1,100,000

LUMBER DESIGN VALUES FOR U.S.

905m. (cont.) DECKING (2" to 4" Thick, 4" and Wider) (Para. 127 only)

Species	Grade	Extreme Fibre in Bending (F_b)	Compression Perpendicular to Grain $F_{C_{perp}}$	Modulus of Elasticity E
		Single Member		
Western Cedars (N)	Select	1200	425	1,100,000
	Commercial	1050		1,000,000
Western White Pine	Select	1100	375	1,400,000
	Commercial	925		1,300,000
Red Pine	Select	1150	440	1,300,000
	Commercial	975		1,200,000
Eastern White Pine (N)	Select	900	350	1,200,000
	Commercial	775		1,100,000
Northern Species	Select	900	350	1,100,000
	Commercial	775		1,000,000
Coast Species	Select	1250	370	1,500,000
	Commercial	1050		1,400,000

Note 1: Allowable fibre stress in bending (F_b) applies only when plank is used flatwise, e.g., when loaded on wide face.

Note 2: See Paras. 905a through 905f for conditions of use and adjustment factors.

LUMBER DESIGN VALUES FOR U.S.

275

905n. BEAMS AND STRINGERS (5" and Thicker, Width more than 2" greater than thickness) (Para. 130)
 Recommended Allowable Unit Stresses (psi)

Species	Grade	Extreme Fibre in Bending F_b Single Member	Tension Parallel to Grain F_t	Horizontal Shear F_v	Compression		Modulus of Elasticity E
					Perp. to Grain $F_{c\perp}$	Parallel to Grain $F_{c\parallel}$	
D Fir-L (N)	Sel Str	1600	950	170	625	1100	1,600,000
	No. 1 Str	1300	675			925	1,600,000
	No. 2 Str	875	425			600	1,300,000
Hem-Fir (N)	Sel Str	1250	725	135	405	900	1,300,000
	No. 1 Str	1000	500			750	1,300,000
	No. 2 Str	675	325			475	1,100,000
Hem-Tam (N)	Sel Str	1450	850	165	555	950	1,300,000
	No. 1 Str	1200	600			800	1,300,000
	No. 2 Str	775	400			500	1,100,000
S-P-F	Sel Str	1100	650	125	425	775	1,300,000
	No. 1 Str	900	450			625	1,300,000
	No. 2 Str	600	300			425	1,000,000
W Hem (N)	Sel Str	1400	825	135	410	1000	1,400,000
	No. 1 Str	1150	575			850	1,400,000
	No. 2 Str	750	375			550	1,100,000

LUMBER DESIGN VALUES FOR U.S.

905n. (cont.) **BEAMS AND STRINGERS** (5" and Thicker, Width more than 2" greater than thickness) (Para. 130)

Coast Sitka Spruce	Sel Str	1150	675			775	1,500,000
	No. 1 Str	950	475	115	455	650	1,500,000
	No. 2 Str	625	325			425	1,200,000
P Pine	Sel Str	1100	725			750	1,100,000
	No. 1 Str	925	500	130	535	625	1,100,000
	No. 2 Str	600	300			400	900,000
Western Cedars (N)	Sel Str	1150	675			850	1,000,000
	No. 1 Str	925	475	130	425	700	1,000,000
	No. 2 Str	625	300			450	800,000
WW Pine	Sel Str	1050	600			775	1,300,000
	No. 1 Str	850	425	120	375	625	1,300,000
	No. 2 Str	550	275			400	1,000,000
R Pine	Sel Str	1050	625			725	1,100,000
	No. 1 Str	875	450	130	440	600	1,100,000
	No. 2 Str	575	300			375	900,000
EW Pine (N), N. Aspen, Black Cottonwood, Northern Species & Coast Species			No stresses provided in NLGA Grading Rules				

Note 1: Allowable fibre stress in bending (F_b) applies only when member is loaded on narrow face.

Note 2: See Paras. 905a through 905h for conditions of use and adjustment factors.

LUMBER DESIGN VALUES FOR U.S.

905o. POST AND TIMBERS (5" x 5" and Thicker, Width not more than 2" Greater than Thickness) (Para. 131)
 Recommended Allowable Unit Stresses (psi)

Species	Grade	Extreme Fibre in Bending F_b	Tension Parallel to Grain F_t	Horizontal Shear F_v	Compression		Modulus of Elasticity E
		Single Member			Perp. to Grain F_{cperp}	Parallel to Grain $F_{c }$	
D Fir-L (N)	Sel Str	1500	1000	170	625	1150	1,600,000
	No. 1 Str	1200	825				
	No. 2 Str	725	475				
Hem-Fir (N)	Sel Str	1150	775	135	405	950	1,300,000
	No. 1 Str	925	625				
	No. 2 Str	550	375				
Hem-Tam (N)	Sel Str	1350	900	165	555	1000	1,300,000
	No. 1 Str	1100	725				
	No. 2 Str	650	425				
S-P-F	Sel Str	1050	700	125	425	800	1,300,000
	No. 1 Str	850	550				
	No. 2 Str	500	325				
W Hem (N)	Sel Str	1300	875	135	410	1100	1,400,000
	No. 1 Str	1050	700				
	No. 2 Str	650	425				

LUMBER DESIGN VALUES FOR U.S.

905o. (cont.) **POST AND TIMBERS** (5" x 5" and Thicker, Width not more than 2" Greater than Thickness) (Para. 131)

Coast Sitka Spruce	Sel Str	1100	725			825	1,500,000
	No. 1 Str	875	575	115	455	725	1,500,000
	No. 2 Str	525	350			500	1,200,000
P Pine	Sel Str	1000	675			800	1,100,000
	No. 1 Str	825	550	130	535	700	1,100,000
	No. 2 Str	475	325			325	900,000
Western Cedars (N)	Sel Str	1050	700			900	1,000,000
	No. 1 Str	875	575	130	425	800	1,000,000
	No. 2 Str	500	350			550	800,000
WW Pine	Sel Str	975	650			800	1,300,000
	No. 1 Str	775	525	120	375	700	1,300,000
	No. 2 Str	450	300			500	1,000,000
Red Pine	Sel Str	1000	675			775	1,100,000
	No. 1 Str	800	550	130	440	675	1,100,000
	No. 2 Str	475	325			475	900,000
EW Pine (N), N. Aspen Black Cottonwood, Northern Species & Coast Species				No stresses provided in NLGA Grading Rules			

LUMBER DESIGN VALUES FOR U.S.

Note 1: If Post and Timber sizes are graded to Beam and Stringer requirements, design values for Beams and Stringers apply.

Note 2: See Paras. 905a through 905f for conditions of use and adjustment factors.

PURPOSELY LEFT BLANK



LUMBER DESIGN VALUES FOR U.S.

910. MACHINE GRADED LUMBER:

2" or less in thickness - 2" & wider

910a. SPECIFIC GRAVITY (SG) ⁽⁴⁾

i) SG for D Fir-L (N): SG values for D Fir-L vary depending on the Grade E values, and are as follows:

Grade E (million psi)	SG Value
1.2 to 1.9	0.49
2.0 to 2.2	0.53
2.3 & higher	0.57

ii) SG for Hem-Fir (N): All Grade E values: 0.46

iii) SG for S-P-F: SG values for S-P-F vary depending on the Grade E values, and are as follows:

Grade E (million psi)	SG Value
1.2 to 1.7	0.42
1.8 to 1.9	0.46
2.0 & higher	0.50

⁽⁴⁾ **Note:** Specific gravity values for all MSR/MEL grades are shown above, unless otherwise qualified by tests and shown on the grade stamp.

910b. HORIZONTAL SHEAR (F_v)

i) F_v for D Fir-L (N): F_v values for D Fir-L vary depending on the grade E values, and are as follows:

Grade E (million psi)	F _v Value
1.2 to 2.2	180 psi
2.3 & higher	190 psi

ii) F_v for Hem-Fir (N): All Grade E values: 145 psi

iii) F_v for S-P-F: F_v values for S-P-F vary depending on the Grade E values, and are as follows:

Grade E (million psi)	F _v Value
1.2 to 1.7	135 psi
1.8 to 1.9	160 psi
2.0 & higher	170 psi

When a grade is qualified by test and daily quality controlled for specific gravity and the SG is shown on the grade stamp, the horizontal shear value may be calculated from the following formula:

$$F_v = 284.8 \times S_g + 26.6 \text{ (psi)}$$

16

LUMBER DESIGN VALUES FOR U.S.

910c. COMPRESSION PERPENDICULAR TO GRAIN ($F_{C_{perp}}$)

i) $F_{C_{perp}}$ for **D Fir-L (N)**: $F_{C_{perp}}$ values for D Fir-L vary depending on the **Grade E** values, and are as follows:

<u>Grade E (million psi)</u>	<u>$F_{C_{perp}}$ Value</u>
1.2 to 1.9	625 psi
2.0 & higher	715 psi

ii) $F_{C_{perp}}$ for **Hem-Fir(N)**: All Grade E values: 405 psi

iii) $F_{C_{perp}}$ for **S-P-F**: $F_{C_{perp}}$ values for S-P-F vary depending on the **Grade E** values, and are as follows:

<u>Grade E (million psi)</u>	<u>$F_{C_{perp}}$ Value</u>
1.2 to 1.7	425 psi
1.8 to 1.9	525 psi
2.0 & higher	615 psi

Compression perpendicular to grain and horizontal shear values, as shown above, are the same as assigned by ASTM methods to visually graded lumber except for S-P-F MSR/MEL grades where indicated which was established using experimental data and relationships between measured properties and $F_{C_{perp}}$ and F_v .

When a grade is qualified by test and daily quality controlled for specific gravity and the **SG** is shown on the grade stamp, the allowable compression perpendicular to grain value may be calculated from the following formula:

$$F_{C_{perp}.04} = 2243.8 \times S_G - 473.8 \text{ (psi)}$$

Note: Calculated values to be rounded to the nearest 5 psi.

Compression perpendicular to grain values are based on a 0.04 inch deformation limit and are standard design for most structures. Values at 0.02 inch deformation can be obtained with the following formula:

$$F_{C_{perp}.02} = 0.71 \times F_{C_{perp}.04} + 15 \text{ (psi)}$$

LUMBER DESIGN VALUES FOR U.S.

910d. MACHINE STRESS-RATED LUMBER (MSR):

2" or less in thickness - 2" & wider

Design Values, psi, normal loading.

Grade Description as per Para. 128a.

MSR Grade	Bending at Extreme F_b	Modulus of Elasticity E	Tension Parallel to Grain F_t	Compression Parallel to Grain $F_{c }$
1200F _b -1.2E	1,200	1,200,000	600	1,400
1350F _b -1.3E	1,350	1,300,000	750	1,600
1450F _b -1.3E	1,450	1,300,000	800	1,625
1500F _b -1.4E	1,500	1,400,000	900	1,650
1650F _b -1.5E	1,650	1,500,000	1,020	1,700
1800F _b -1.6E	1,800	1,600,000	1,175	1,750
1950F _b -1.7E	1,950	1,700,000	1,375	1,800
2100F _b -1.8E	2,100	1,800,000	1,575	1,875
2250F _b -1.9E	2,250	1,900,000	1,750	1,925
2400F _b -2.0E	2,400	2,000,000	1,925	1,975
2550F _b -2.1E	2,550	2,100,000	2,050	2,025
2700F _b -2.2E	2,700	2,200,000	2,150	2,100
2850F _b -2.3E	2,850	2,300,000	2,300	2,150
3000F _b -2.4E	3,000	2,400,000	2,400	2,200

The following grades provide a modulus of elasticity with higher corresponding strengths. For these MSR grades, qualification and daily quality control for tensile strength are required.

MSR Grade	Bending at Extreme F_b	Modulus of Elasticity E	Tension Parallel to Grain F_t	Compression Parallel to Grain $F_{c }$
1400F _b -1.2E	1,400	1,200,000	800	1,600
1600F _b -1.4E	1,600	1,400,000	950	1,675
1650F _b -1.3E	1,650	1,300,000	1,020	1,700
1800F _b -1.5E	1,800	1,500,000	1,300	1,750
2000F _b -1.6E	2,000	1,600,000	1,300	1,825
2250F _b -1.7E	2,250	1,700,000	1,750	1,925
2250F _b -1.8E	2,250	1,800,000	1,750	1,925
2400F _b -1.8E	2,400	1,800,000	1,925	1,975

i) The grade MOE is assigned in increments of 100,000 psi.

Note: Grades of MSR may be produced with alternate design stress assignments when provided for in the NLGA rules.

LUMBER DESIGN VALUES FOR U.S.

910e. MACHINE EVALUATED LUMBER (MEL):

2" or less in thickness - all widths

Design Values, psi, normal loading.

Grade Description as per Para. 128b.

MEL Grade	Bending at Extreme F_b	Modulus of Elasticity E	Tension Parallel to Grain F_t	Compression Parallel to Grain F_{cl}
M - 10	1,400	1,200,000	800	1,600
M - 11	1,550	1,500,000	850	1,675
M - 12	1,600	1,600,000	850	1,675
M - 13	1,600	1,400,000	950	1,675
M - 14	1,800	1,700,000	1,000	1,750
M - 15	1,800	1,500,000	1,100	1,750
M - 18	2,000	1,800,000	1,200	1,825
M - 19	2,000	1,600,000	1,300	1,825
M - 21	2,300	1,900,000	1,400	1,950
M - 22	2,350	1,700,000	1,500	1,950
M - 23	2,400	1,800,000	1,900	1,975
M - 24	2,700	1,900,000	1,800	2,100
M - 25	2,750	2,200,000	2,000	2,100
M - 26	2,800	2,000,000	1,800	2,150

- i) MEL allowable stresses are assigned in the following increments:

Mechanical Property	Increment
Modulus of Elasticity (MOE)	100,000 psi
Fiber Stress in Bending (F_b)	50 psi
Fiber Stress in Tension (F_t)	50 psi
Compression Parallel to Grain (F_{cl})	25 psi
Compression Perpendicular to Grain ($F_{c\perp}$)	5 psi

Note: Grades of MEL may be produced with alternate design value assignments when provided for in the NLGA rules.



PURPOSELY LEFT BLANK



16

285





General Instruction No. 1

**NLGA Standard Grading Rules
for Canadian Lumber**

August 1, 2017

NLGA Standard Grading Rules for Canadian Lumber consists of **284** pages plus the NLGA Interpretations & EU Export Annex.

This book like all NLGA Standards, is subject to periodic review, and may be amended from time to time.

Check the publication section of the website (www.nlga.org) for the date of the latest edition of NLGA Standard Grading Rules for Canadian Lumber.

