## Erratum No. 1 to the NLGA Standard Grading Rules for Canadian Lumber (2022)

(effective March 21, 2023)

**Note:** This Erratum corrects the Para. 124d, NO. 3 Structural grade, Knot table for the permitted sizes of unsound or loose knots and holes for nominal 6" width and wider, as follows:

## 124d. "NO. 3" STRUCTURAL

Characteristics permitted and limiting provisions shall be:

- **Checks** seasoning checks not limited. Through checks at ends are limited as splits.
- **Knots** well spaced knots of any quality are permitted in the following sizes or their equivalent displacement:

Nominal Width	At Edge Wide Face	Centreline Wide Face	Unsound or Loose Knots and Holes* (Any Cause)
2"	3⁄4"	3⁄4"	3⁄4"
3"	1 ¼"	1 ¼"	1 ¼"
4"	1 ¾"	2 ½"	1 ¾"
5"	2 ¼"	3"	1 1%"
6"	2 ¾"	3 ¾"	<del>1½"</del> 2"
8"	3 ½"	4 ½"	<del>2"</del> 2½"
10"	4 1⁄2"	5 ½"	<del>2 ½</del> 3"
12"	5 ½"	6 ½"	<del>3"</del> <u>3 ½"</u> -
14"	6"	7"	<del>3 ½"</del> 4"
16"	6 <b>¾</b> "	8"	4 <del>"</del> 4 ½"
18"	6 ½"	8 ¼"	<u>4 ½"</u> 5"

\*One hole or equivalent smaller holes per 1 lineal ft.