## Erratum No. 4 to the NLGA Standard Grading Rules for Canadian Lumber (2022) (effective May 30, 2024)

**Note:** This Erratum corrects

• Para. 124b, NO. 1 Structural, knot table for the permitted sizes of knots at the edge of wide face for nominal 8" width and wider, as follows:

## 124b. "NO. 1" STRUCTURAL

Characteristics permitted and limiting provisions shall be:

**Checks** surface seasoning checks, not limited. Through checks at ends are limited as

splits.

**Knots** sound, firm; encased and pith knots, if tight and well spaced, are permitted in

sizes not to exceed the following or equivalent displacement:

Nominal Width	At Edge Wide Face	Centreline Wide Face	Unsound or Loose Knots and Holes* (Any Cause)
2"	1/2"	1/2"	1/2"
3"	3/4"	3/4"	3/4"
4"	1"	1 ½"	1"
5"	1 ¼"	1 %"	1 1/8"
6"	1 ½"	2 ¼"	1 ¼"
8"	2" <del>1 ½"</del>	2 ¾"	1 ½"
10"	2 ½" <del>1 %"</del>	3 ¼"	1 ½"
12"	3 " <del>2 ¼"</del>	3 ¾"	1 ½"
14"	3 1/8" 2 3/8"	4"	1 ½"
16"	3 ¼" <del>2 ¾"</del>	4 ½"	1 ½"
18"	3 3/8" 2 1/2"	4 %"	1 ½"

<sup>\*</sup>One hole or equivalent smaller holes per 3 lineal ft.